

AQUAROC[®] CEMENT BOARD

Technical Data Sheet

Characteristics:

Composition:

Cement core lightened with polystyrene beads and with a glass grid on each side. Exposed face treated to reduce porosity.

Type of edge: SE (square edge) on all 4 sides

Thickness in mm: 12.5

Dimensions: 1200 x 2400

Surface mass: 13.50 kg/m² (or 1.080 kg/m³)

Heat resistance: 0.062 m².K/w

Tolerances in mm: Thickness: ± 0,5
Width (mm): -5 / +0
Length: -5 / +0

Reaction to fire: A2-s1,d0
(test report CSTB RA07-0485)

Surface hardness: High surface hardness in accordance with EN 520 standard

Water resistance: Excellent

Fire resistance: Normal

Use:

Intended for the creation of framework partition walls in areas with high hygrometry levels (classified as EB+ areas for collective use or EC areas).



Freephone ROI: 1800 744480

Freephone NI: 0845 3990159

Email: tech.ie@saint-gobain.com

www.gyproc.ie

Gyproc, Gypframe and Glasroc are all registered trade names of Saint-Gobain Construction Products (Irl) Limited. Isover is a registered trade name of Saint-Gobain.

Saint-Gobain Construction Products (Irl) Limited reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation. For a comprehensive and up-to-date library of information visit the Gyproc website at: www.gyproc.ie