



PRODUCT DATA SHEET

GYP FINISHER ULTRA

Overview

Gyproc Gyp Finisher Ultra is a ready mixed joint compound for filling and finishing plasterboard joints with an even smoother finisher and even lower dust produced compared to our Gyproc Gyp Finisher.

Applications

Gyproc Gyp Finisher Ultra is to be used by hand or mechanically for the filling and finishing steps in the traditional three stage jointing process.

Also suitable for spray application using airless spraying equipment.

Standards

Gyproc Gyp Finisher Ultra is classified under EN 13963 as type 3A, i.e. an air drying compound for finishing.

Performance

Effect of temperature

All buckets must be protected from freezing and frozen substrates are forbidden. Gyproc Gyp Finisher Ultra application is only suitable for situations where the temperature does not exceed 49°C.

Effect of condensation and other moisture

Gyproc Gyp Finisher Ultra should be protected from continuous exposure to moisture. Prolonged or repeated exposure to moisture may cause a loss of strength and/or adhesion.

Coverage

0.25 kg/m² to 1.7 kg/m² depending on the thickness

Water requirement

See Installation - "Mixing"

Minimum temperature

Do not apply at temperatures below 5°C or above 30°C, or at humidity levels above 75%.

Pallet quantity

33 X 20kg buckets = 660 kg

Installation

Background preparation

Plasterboard or Gyproc Gyp Filler surfaces should be reasonably dry, clean and and only installed in weather-tight buildings with appropriate ventilation. Boards should be securely fixed with no steps between adjacent boards. The correct fixings must be used and properly located with their heads just below the liner surface. Any protruding screw heads should be driven home with a hand screwdriver prior to plastering.

Storage

Buckets should be stored in a dry and cool place. Absolutely avoid frost at any stage during storage. Gyp Finisher Ultra stored correctly in a non-opened packaging has a shelf life of 12 months.

Mixing

Gyproc Gyp Finisher Ultra is supplied ready mixed with water, at a consistency suitable for hand application. Stir before use. For any mechanical application, only dilute if necessary and using no more than 0.25 litres per bucket. Excessive dilution increases shrinkage and drying times, and reduces strength. Excessive mechanical mixing should be avoided and only low-speed mixers used.

Once opened, material should be used within a week, if protected from drying out or contamination by other materials.

Application

Apply Gyproc Gyp Finisher Ultra to fill in a joint or on top of a filled joint. Allow to completely dry, then apply a final coat, feathered out beyond the second.

Finishing

After the finishing coat has dried, sand slightly to remove trowel marks, etc. Apply Drywall Primer to the whole surface to prepare the surface for painting, or Gyproc Drywall Sealer in one coat to prepare for wallpapering or two coats to provide a vapour check.

Decoration

Apply decoration with the minimum of delay after Gyproc Drywall Primer or Gyproc Drywall Sealer has dried. As with all wall and ceiling areas, gloss or high-sheen finishes will highlight any variation of the surface, particularly with shallow-angle lighting. The use of low-sheen or matt finishes minimises this risk. Jointing should be carried out under similar lighting conditions to those used for subsequent inspection and use.

Heavy, semi-rigid or impermeable wallcoverings may involve specialist adhesives or techniques which may not be compatible with Gyproc Drywall Primer or Gyproc Drywall Sealer. Consult the wallcovering and/or adhesive manufacturer for a specific recommendation. Impermeable wallcoverings fixed with waterbased adhesives should not be applied over Gyproc Drywall Sealer, as the drying of the adhesive will be severely restricted.

Maintenance

If the product is correctly applied and not exposed to moisture or mechanical damage, it should not require any form of maintenance.

Technical information:

Binder	Styrene acrylic polymer
Solvent	Water
Aggregate	Carbonates, perlites
Particle size	Max. 100mm
Bulk density	1.2 ± 1%
Non-volatile matter	Approx 60% by weight
Ph	9.0 ± 0.5
Colour	Cream
Building capacity	Very good
Drying time	12/48h depending on the thickness of the layer, the temperature and the humidity of the atmosphere
Conditions of application	Do not apply at temperatures below 5°C or above 30°C, or at humidity levels above 75%
Consumption	0.25 kg/m ² to 1.7 kg/m ² depending on thickness
Max. Layer thickness	5mm
Flammability	Reaction to Fire Classification A2, s1-d0
Cleaning	With water after use

Freephone ROI: 1800 744480

Freephone NI: 0845 3990159

Email: tech.ie@saint-gobain.com

www.gyproc.ie

Gyproc, Gyproframe and Glasroc are all registered trade names of Saint-Gobain Construction Products (Irl) Limited. Isover is a registered trade name of Saint-Gobain.

Saint-Gobain Construction Products (Irl) Limited reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation.

For a comprehensive and up-to-date library of information visit the Gyproc website at: www.gyproc.ie



© Saint-Gobain Construction Products (Irl) Limited
September 2025 | PDS_DSA_GYP_FINISHER_ULTRA

