

Product information

Gyproc ProMix Finish

Instructions

Gyproc ProMix Finish is ready mixed filler for joint and surface filling and finishing on plasterboard. Also recommended for use on already painted surfaces.

Joints or surfaces to be filled should be well attached, cleaned and dry.

Apply by hand or machine at a recommended minimum temperature of +10°C and max 80% RH.

Apply Gyproc ProMix Finish in the joint by hand or machine, place Gyproc Joint Tape in the filler and immediately apply another thin layer on top and let dry. Use Gyproc ProMix Finish for a second filling and final surface finishing. For plasterboard surface filling and finishing initially apply a first layer of Gyproc ProMix Finish and let dry. To achieve best result apply a thin layer on top. Finally smooth with sandpaper particle size 100-120. Use eye protection.

Storing

Store in a cool place but protected from frost. Filler is perishable and is therefore marked with a best-before date for unopened packaging.

Technical data

Binder: Latex copolymer
Solvent: Water
Aggregate: Perlite
Particle size: Max 0.2 mm
Density: 1,2 kg/litre
Vol. non-volatile: Approx. 55%
pH: Approx 9
Colour: White
Build: High
Drying time: 8-10 hours depending on layer thickness and temperature.
Consumption: Joint filling and finishing: 0,3 l/m²
Surface finishing 1 mm thickness layer – 1 litre/m²
Thickness layer: Max 4 mm
Flammability: Does not spread or support fire
Cleaning: Use water to clean tools



Gyproc AB
PO Box 153
SE-746 24 Bålsta
Phone +46 171 41 54 60 Order
Phone +46 171 41 54 80 Gyproc Teknisk Support
Fax +46 171 41 54 50
www.gyproc.se

A Saint-Gobain company

May2009. ©Gyproc.

