



PRODUCT DATA SHEET

SOUNDBLOC

Introduction

Gyproc SoundBloc is designed for use in Gyproc wall and partition systems where greater levels of sound insulation are required.

Product Description

Gypsum plasterboard with a higher density core. Gyproc SoundBloc consists of an aerated gypsum core encased in, and firmly bonded to, strong paper liners. Gyproc SoundBloc is a plasterboard that is suitable for drylining internal surfaces.

This plasterboard is one of the products within our plasterboard range that is certified to BES 6001 achieving a rating of 'Excellent'.

Board Performance

Fire protection

Plasterboard linings provide good fire protection owing to the unique behaviour of the noncombustible gypsum core when subjected to high temperatures. For the purposes of the national Building Regulations, plasterboard is designated a 'material of limited combustibility' (Technical Guidance Document B). The surfaces of Gyproc SoundBloc are designated Class 0 (for the purposes of national Building Regulations). Please refer to the table below.

Fire resistance

Please refer to the Gyproc **White Book** product or systems section for information on the fire resistance of building elements lined with Gyproc SoundBloc.

Reaction to fire test performance

STANDARD	PERFORMANCE
BS 476: Part 6: 1989 Method of test for fire propagation for products.	Index of performance (I) not exceeding 12 and a sub-index (i1) not exceeding 6.
BS 476: Part 7: 1997 Surface spread of flame tests for materials.	Class 1 (both sides).
EN 520: 2004, A1:2009.	Classified without further testing as A2-s1, d0.

Thermal conductivity

Ⓐ Gyproc SoundBloc - 0.25W/mK

Effect of temperature

Gyproc SoundBloc is unsuitable for use in areas subject to continuously damp or humid conditions and must not be used to isolate dampness. Plasterboards are not suitable for use in temperatures above 49°C, but can be subjected to freezing conditions without risk of damage.

Effect of condensation

The thermal insulation and ventilation requirements of national Building Regulations aim to reduce the risk of condensation and mould growth in new buildings. However, designers should take care to eliminate all possibility of problems caused by condensation, particularly in refurbishment projects.

Board Performance continued

Board colour

- Blue face paper
- Brown reverse side paper

Board printing

- Face** No print
- Edge** No print
- Reverse** Product information, compliance standards and certifications.

Board range

WIDTH MM	LENGTH MM	EDGE TYPE
12.5mm Board		kg/m ² = 11.4 R (m ² K/W) = 0.05
1200	2438 2700 3000	T/E
15mm Board		kg/m ² = 14 R (m ² K/W) = 0.06
1200	2400 2700 3000	T/E

T/E = Tapered Edge

Board types

T/E - with Gyproc branded jointing material used with Gyproc Paper Joint Tape.

Application and installation

General

It is important to observe appropriate health and safety legislation when working on site i.e. personal protective clothing and equipment, etc. The following notes are intended as general guidance only. In practice, consideration must be given to design criteria requiring specific project solutions.

Handling

Manual off-loading of this product should be carried out with care to avoid unnecessary strain. For further information please refer to the Manual Handling section of the **Installation Guide** available to download from www.gyproc.ie.

Cutting

This product may be cut using a plasterboard saw or by scoring with a sharp knife and snapping the board over a straight edge. Holes for switch or socket boxes should be cut out before the boards are fixed using a utility saw or sharp knife. When cutting boards, power and hand tools should be used with care and in accordance with the manufacturers' recommendations. Power tools should only be used by people who have been instructed and trained to use them safely. Appropriate personal protective equipment should be used.

Fixing

Fix boards with decorative side out to receive joint treatment or a skim plaster finish. Lightly butt boards together. Never force boards into position. Install fixings not closer than 13mm from cut edges and 10mm from bound edges. Position cut edges to internal angles whenever possible, removing paper burrs with fine sandpaper. Stagger horizontal and vertical board joints between layers by a minimum of 600mm. Locate boards to the centre line of framing where this supports board edges or ends.

Jointing

Gyproc jointing materials produce durable joint reinforcement and a smooth, continuous, crack-resistant surface ready for priming and final decoration. A number of jointing specifications are available to suit the board type, method of application, and site preference.

Plastering

The face (blue) of Gyproc SoundBloc can be plastered with either Gyproc Skimcoat, Carlite Ultra Finish or Carlite Finish. There should be the minimum of delay between completion of the lining and the commencement of plastering.

Decoration

After the joint treatment has dried, decoration, including any decorator's preparatory work, should follow with the minimum delay.

Product standards

EN520: 2004, A1:2009 Gypsum Plasterboards, definitions, requirements and test methods

Type D: Gypsum plasterboard with control density.

These boards have a controlled density, with a face to which suitable gypsum plasters or decoration may be applied. This enables improved performance in certain applications to be obtained.

Maintenance

Repair

Minor damage - Lightly sand the surface to remove burrs and fill flush with Gyproc Joint Filler or Gyproc Gyp Filler. When dry, apply Gyproc Drywall Primer to leave the surface ready for decoration.

Deep indents resulting from impact - Check the plasterboard core to ensure that it is not shattered. If intact, apply a coat of Gyproc Joint Filler, or Gyproc Gyp Filler, followed by the procedure for repairing minor damage as outlined above, once set/dry.

Damaged core and / or broken edges (non-

performance situations only) - Remove the damaged area of core. Score the liner approximately 10mm away from the sound plaster around the damaged area, and peel the paper liner away. Apply GypPrime or PVA to seal the core and surrounding liner. Bulk fill the hole with a stiff mix of Gyproc Gyp Filler or Gyproc Joint Filler, and strike off flush. Apply Gyproc Gyp Filler or Gyproc Joint Filler, once the filler is set/dry. When dry, apply Gyproc Drywall Primer.

Extensive damage - When the damage is more extensive, it may be necessary to replace that area of plasterboard. It is important that the replacement board is of the same type as specified and installed. Cut out the affected area back to the nearest framing member. Replace the plasterboard, accurately cutting and screw fixing the same type and thickness of plasterboard. Fill edge joints, then tape and finish in the recommended way. Treat the finished surface with Gyproc Drywall Primer. Redecorate as required.

NB It is essential that repairs are made 'like for like'. If the finish is skim plaster, jointing materials must not be used in the repair.

Freephone ROI: 1800 744480

Freephone NI: 0845 3990159

Email: tech.ie@saint-gobain.com

www.gyproc.ie

Gyproc, Gypframe and Glasroc are all registered trade names of Saint-Gobain Construction Products (Irl) Limited. Isover is a registered trade name of Saint-Gobain.

Saint-Gobain Construction Products (Irl) Limited reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation.

For a comprehensive and up-to-date library of information visit the Gyproc website at: www.gyproc.ie



© Saint-Gobain Construction Products (Irl) Limited
November 2023 | GYPIRL_SB_PDS_202311

 gyproc
SAINT-GOBAIN

 SAINT-GOBAIN