

# AQUAROC<sup>®</sup> CEMENT BOARD

## Technical Data Sheet

### Characteristics:

#### Composition:

Cement core lightened with polystyrene beads and with a glass grid on each side. Exposed face treated to reduce porosity.

**Type of edge:** SE (square edge) on all 4 sides

**Thickness in mm:** 12.5

**Dimensions:** 1200 x 2400

**Surface mass:** 13.50 kg/m<sup>2</sup> (or 1.080 kg/m<sup>3</sup>)

**Heat resistance:** 0.062 m<sup>2</sup>.K/w

**Tolerances in mm:** Thickness: ± 0,5  
Width (mm): -5 / +0  
Length: -5 / +0

**Reaction to fire:** A2-s1,d0  
(in accordance with EN 13501-1)

**Surface hardness:** High surface hardness in accordance with EN 520 standard

**Water resistance:** Categories A and B in accordance with EN 12467:2012 section 5.4.5

#### Use:

Intended for the creation of framework partition walls in areas with intermittently high humidity levels (classified as EB+ areas for collective use or EC areas).



**Freephone ROI:** 1800 744480

**Freephone NI:** 0845 3990159

**Email:** tech.ie@saint-gobain.com

**www.gyproc.ie**

Gyproc, Gypframe and Glasroc are all registered trade names of Saint-Gobain Construction Products (Irl) Limited. Isover is a registered trade name of Saint-Gobain.

Saint-Gobain Construction Products (Irl) Limited reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation. For a comprehensive and up-to-date library of information visit the Gyproc website at: [www.gyproc.ie](http://www.gyproc.ie)