



## PRODUCT DATA SHEET

# GYPROC GLASROC X

### Overview

Glasroc X is a gypsum board specifically designed to provide external weather protection to structural frame steel constructions prior to the installation of the finished exterior façade system.

Glasroc X contributes to moisture, weather resistance and fire performance. Combined with a dimensional stability performance this sheathing board makes an alternative to cement particle boards.

## Product Description

Glasroc X is a gypsum board with mat reinforcement which has inherent mould resistant properties. The glass fibre mat protects the board with its hydrophobic coating, and has additional UV resistant properties.

## Performance

### Moisture resistance

Glasroc X meets EN 15283-1 GM-H1 gypsum boards with mat reinforcement with reduced water absorption rate not greater than 5%.

### Fire resistance

Please refer to the Glasroc X product brochure for information on the fire resistance of building elements lined with Glasroc X.

Glasroc X meets EN 15283-1 GM-F gypsum boards with mat reinforcement with improved core cohesion at high temperature.

### Reaction to fire test performance

Gyproc Glasroc X is classified as A1 in accordance with EN 13501-1: 2007 + A1: 2009

### Thermal conductivity

$\lambda$  Glasroc X - 0.25W/mK

### Limitations of use

Glasroc X boards are not suitable for use in temperatures above 45°C, but can be subjected to freezing conditions without risk of damage.

### Effect of condensation

The thermal insulation and ventilation requirements of the National Building Regulations aim to reduce the risk of condensation and mould growth in new buildings. However, designers should take care to eliminate all possibility of problems caused by condensation, particularly in refurbishment projects.

### Board colour

- White face paper with blue printing
- White reverse side paper

### Board printing

**Face** Branding and logos.

**Edge** Product code, EAN number, board thickness x width x length, edge type.

**Reverse** Standard and certification.

## Board range

WIDTH MM	LENGTH MM	EDGE TYPE
<b>12.5mm Board</b> 1200	2400	kg/m <sup>2</sup> = 10.9 λ (W/mK) = 0.19 S/E
<b>15mm Board</b> 1200	2400	kg/m <sup>2</sup> = 13.10 λ (W/mK) = 0.19 S/E

S/E = Square Edge

## Application and installation

### General

It is important to observe appropriate health and safety legislation when working on site i.e. personal protective clothing and equipment, etc. The following notes are intended as general guidance only. In practice, consideration must be given to design criteria requiring specific project solutions.

### Storage

The boards must be stored on a firm, flat and level surface. If the boards are temporarily stored outside they must be sufficiently supported off the ground and covered by a securely anchored polythene sheet or tarpaulin to protect them from dampness, weather, contamination and mechanical damage e.g. from construction traffic.

### Handling

Manual off-loading of this product should be carried out with care to avoid unnecessary strain. For further information please refer to the Manual Handling section of the Site Book, available to download from [www.gyproc.ie](http://www.gyproc.ie).

## Cutting

This product may be cut using a plasterboard saw or by scoring with a sharp knife and snapping the board over a straight edge. When cutting boards, power and hand tools should be used with care and in accordance with the manufacturers' recommendations. Power tools should only be used by people who have been instructed and trained to use them safely. Appropriate personal protective equipment should be used.

### Fixing

Fix boards with printed side out to ensure the required weather protection and UV performance. Lightly butt boards together. Never force boards into position.

### Fixing

**NB** Glasroc X Screws should be installed flush to the surface of the board. If overtightened, Glasroc X Sealant should be applied to cover the head.

### Jointing

Glasroc X Sealant is used as the tested jointing material to maintain the fire resistance performances of Glasroc X systems.

## Product standards

EN 15283-1 Type GM – F and H1

Freephone ROI: 1800 744480

Freephone NI: 0845 3990159

Email: [tech.ie@saint-gobain.com](mailto:tech.ie@saint-gobain.com)

[www.gyproc.ie](http://www.gyproc.ie)

Gyproc, Gypframe and Glasroc are all registered trade names of Saint-Gobain Construction Products (Irl) Limited. Isover is a registered trade name of Saint-Gobain.

Saint-Gobain Construction Products (Irl) Limited reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation.

For a comprehensive and up-to-date library of information visit the Gyproc website at: [www.gyproc.ie](http://www.gyproc.ie)



© Saint-Gobain Construction Products (Irl) Limited  
May 2025 | PDS\_SB\_GLASROC-X

